



<b>BACKING</b>	<b>100% Cotton Knitted</b>
<b>BIO- CONTENT</b>	<b>73% BIO-BASED</b> COMPOSITION VARIABILITY $\pm 3\%$
<b>THICKNESS</b>	<b>1.15 mm</b>

### Note

Orders for rolls available in stock will be shipped in about 4-5 days

Custom orders will be shipped in about 25-30 days

We can custom any color

Terratan™ is made in India

### Add on Properties

Flame Retardency

Anti-Fungal

Heat Resistance

Breathability

## TECH DATA SHEET

TEST TYPE	RESULT	UNIT	STANDARD
TENSILE STRENGTH (ALONG)	210	N/5CM	ISO 1421
TENSILE STRENGTH (ACROSS)	470	N/5CM	ISO 1421
TEAR STRENGTH (ALONG)	26	N	ISO 3377
TEAR STRENGTH (ACROSS)	27	N	ISO 3377
ADHESION - ALONG	>25	N/5CM	ISO 7016
BALLY FLEX CYCLES	>60,000	CYCLES	ISO 5402
ABRASION TEST (DRY)	>1,50,000	CYCLES	ISO 12947
ABRASION TEST (WET)	>20,000	CYCLES	ISO 12947
COLOR FASTNESS TO RUBBING	>4	GREY SCALE	ISO 105-X12
COLOR FASTNESS TO LIGHT	>5	BLUE SCALE	ISO 105-B02
ELONGATION AT BREAK (ALONG)	300	%	ISO 1421
ELONGATION AT BREAK (ACROSS)	67	%	ISO 1421
PEEL OFF	1.6	N/MM	ISO 2411

Data are the result of our know-how and are to be considered correct, however, considering the variability of applications, the suitability of the product is user's responsibility.

These test results are as observed and recorded in our lab